

L3 ANSWER 1 OF 1 CAPLUS COPYRIGHT 2007 ACS on STN
 ACCESSION NUMBER: 1974:426257 CAPLUS Full-text
 DOCUMENT NUMBER: 81:26257
 TITLE: Polyester
 INVENTOR(S): Kobayashi, Fumio; Matsukura, Kazuo; Tomita, Kosuke;
 Yamaguchi, Ryoza
 PATENT ASSIGNEE(S): Unitika Ltd.
 SOURCE: Jpn. Tokkyo Koho, 3 pp.
 CODEN: JAXXAD
 DOCUMENT TYPE: Patent
 LANGUAGE: Japanese
 FAMILY ACC. NUM. COUNT: 1
 PATENT INFORMATION:

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
-----	-----	-----	-----	-----
JP 48031991	B	19731003	JP 1967-68190	19671023 <--
PRIORITY APPLN. INFO.:			JP 1967-68190	19671023

AB Polyesters with increased transparency are prepared by polycondensing dimethyl terephthalate (I) with ethylene glycol (II), in combination with or without Me p-(β -hydroxyethoxy)benzoate, in the presence of known polycondensation catalysts (antimony trioxide [1309-64-4] or germanium dioxide [1310-53-8]), alkaline earth metal compds., and selenium dioxide [7446-08-4] or selenic acid [7783-08-6]. Thus, a mixture of I 1, II 2, and Ca(OAc)2 8 .tim. 10-4 mole was heated 5 hr at 180-210.deg. under N, mixed with 8 .tim. 10-4 mole SeO2 and 2 .tim. 10-4 mole Sb2O3, and heated 4 hr at 280.deg./0.1mm, giving colorless poly(ethylene terephthalate) [25038-59-9] with intrinsic viscosity (1:1 PhOH-C2H2Cl4, 20.deg.) 0.87.